Primary lithium batteries LS 26500

3.6V Primary lithium-thionyl chloride (Li-SOCI₂) High energy C-size bobbin cell

For applications requesting good voltage response and operating life in -60°C/+85°C environments.



Key features

- High and stable operating voltage
- Low self-discharge rate (less than 1% after 1 year of storage at +20°C)
- Stainless steel container
- Hermetic glass-to-metal sealing
- Built-in safety vent
- Finish with or without flat positive end
- Non-flammable electrolyte
- Compliant with IEC 86-4 safety standard and EN 50020 intrinsic safety standard
- Underwriters Laboratories (UL)
 Component Recognition
 (File Number MH 12609)
- Restricted for transport (Class 9)

Main applications

- Utility metering
- Automatic meter readers
- Buoys
- Measuring equipment
- Industrial applications
- Professional electronics

etc...

Storage

Operating temperature range

Optional upon request

Low magnetic version

Cell size references	UM2 - R14 - C
Electrical characteristics	
(typical values relative to cells stored for one year or less at + 30°C max.)	
Nominal capacity (at 4 mA + 20°C 2.0V cut off. The capacity restored by the cell varies according to current drain, temperature and cut off).	7.7 Ah
Open circuit voltage (at + 20°C)	3.67V
Nominal voltage (at 0.5 mA + 20°C)	3.6V
Pulse capability: Typically up to 300 mA (300 mA/0.1 second pulses, drained every 2 mn at +20°C from undischarged cells with 10 µA base current, yield voltage readings above 3.0V. The readings may vary accordito the pulse characteristics, the temperature, and the cell's previous histofitting the cell with a capacitor may be recommended in severe conditions Consult Saft)	ory.
Continuous current permitting 50% of the nominal capacity to be achieved at +20°C with 2.0V cut off. (Higher currents possible, consult Saft)	150 mA

(recommended)

(Operation above ambient T may lead to reduced capacity and

lower voltage readings at the beginning of pulses. Consult Saft)

Physical characteristics	
Diameter (max)	26.0 mm (1.02 in)
Height (max)	49.1 mm or 50.4 mm (1.93 in or 1.98 in) depending on finish type
Typical weight	48 g (1.7 oz)
Li metal content	approx. 2.0 g
Available termination suffix CNR 3 PF, 3 PI CNA (AX) FL	radial tabs F RP radial pins axial leads flying leads etc.

(for more severe conditions, consult Saft)




+ 30°C (+ 86°F) max


- 60°C/+ 85°C

(-76°F/+185°F)

LS 26500



Finished version with protruding positive end cap



Finished version with flat positive end cap

Dimensions in mm.

Storage

• The storage area should be clean, cool (not exceeding + 30°C), dry and ventilated.


Warning

- Fire, explosion and severe burn hazard.
- · Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell.


Saft

12, rue Sadi Carnot 93170 Bagnolet - France Tel +33 1 49 93 19 18 Fax +33 1 49 93 19 69


www.saftbatteries.com



Voltage plateau versus Current and Temperature (at mid-discharge)



Typical discharge profiles at +20°C



Restored Capacity versus Current and Temperature (2.0V cut off)

Doc. Nº 31016-2-0904 Published by the Communications Department

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2-0604. Produced by Arthur Associates

Société anonyme au capital de 31 944 000 $\[mathbb{E}$ RCS Bobigny B 383 703 873

